**BARD Research Grant
Final Scientific Report**

Final report

BARD Project Number:
Feasibility Study IS-3712-05

August 05 – July 06

Date of Submission of the report:
08.2006

Project Title: Development of Agricultural Sensors Based on Conductive Polymers

Investigators

Institutions

Principal Investigator (PI):

Dr. M. Bendikov

Weizmann Institute of Science

Co-Principal Investigator (Co-PI):

Professor Thomas C. Harmon

University of California, Merced

Collaborating Investigators:

Keywords *not* appearing in the title and in order of importance. Avoid abbreviations.
Agricultural sensors, soil and water monitoring, conductive polymers, nitrate monitoring

Abbreviations **commonly** used in the report, in alphabetical order:

Budget: IS: \$59,000

US: \$41,000

Total: \$100,000

Signature
Principal Investigator

Signature
Authorizing Official, Principal Institution

BARD Research Grant Final Scientific Report

Publication Summary (numbers)

	Joint IS/US authorship	US Authors only	Israeli Authors only	Total
Refereed (published, in press, accepted) BARD support acknowledged			2	
Submitted, in review, in preparation				
Invited review papers				
Book chapters				
Books				
Master theses				
Ph.D. theses				
Abstracts				
Not refereed (proceedings, reports, etc.)				

Postdoctoral Training: List the names and social security/identity numbers of all postdocs who received more than 50% of their funding by the grant.

Dr. Sanjio S. Zade

Cooperation Summary (numbers)

	From US to Israel	From Israel to US	Together, elsewhere	Total
Short Visits & Meetings	1	1		2
Longer Visits (Sabbaticals)				-

Description Cooperation:

The Israeli team developed new sensors, while in parallel the US team developed the sensor packaging and deployment techniques. Close collaboration on a unique combination of synthetic organic chemistry, sensor development and field testing was critical to our success. The nature of this research clearly demands input from both teams, one from the fundamental chemistry side of the problem, the other from the environmental deployment side of the problem. Visits by the Israeli team to Merced (Feb 2006) and the U.S. team to Rehovot (July 2006) were crucial to knowledge transfer and the overall success of this highly collaborative effort. Either team alone would never produce a nitrate sensor working in real soils.

Patent Summary (numbers)

	Israeli inventor only	US inventor only	Joint IS/US inventors	Total
Submitted				
Issued (allowed)				
Licensed				

BARD Research Grant Final Scientific Report

Abstract.

In this 1-year feasibility study, we tried polymerization of several different monomers, commercial as well as novel, specially designed and synthesized for this project in the presence of the nitrate ion to produce imprinted conductive polymers. Polymers 1 and 2 (shown below) produced a response to nitrate, but one inferior to that produced by a polypyrrole (Ppy)-based sensor (which we demonstrated prior to this study). Thus, we elected to proceed with improving the stability of the Ppy-based sensor.

In order to improve stability of the Ppy-based sensor, we created a two-layer design which includes nitrate-doped Ppy as an inner layer, and nitrate-doped PEDOT as the outer layer. PEDOT is known for its high environmental stability and conductivity. This design has demonstrated promise, but is still undergoing optimization and stability testing.

Previously we had failed to create nitrate-doped PEDOT in the absence of a Ppy layer. Nitrate-doped PEDOT should be very promising for sensor applications due to its high stability and exceptional sensing properties as we showed previously for sensing of perchlorate ions (by perchlorate-doped PEDOT). During this year, we have succeeded in preparing nitrate-doped PEDOT (4 below) by designing a new starting monomer (compound 3 below) for polymerization. We are currently testing this design for nitrate sensing.

In parallel with the fabrication design studies, we fabricated and tested nitrate-doped Ppy sensors in a series of flow studies under laboratory and field conditions. Nitrate-doped Ppy sensors are less stable than is desirable but provide excellent nitrate sensing characteristics for the short-term experiments focusing on packaging and deployment strategies. The fabricated sensors were successfully interfaced with a commercial battery-powered self-logging (Onset Computer Hobo Datalogger) and a wireless data acquisition and transmission system (Crossbow Technologies MDA300 sensor interface and Mica2 wireless mote). In a series of flow-through experiments with water, the nitrate-doped Ppy sensors were exposed to pulses of dissolved nitrate and compared favorably with an expensive commercial sensor. In 24-hour field tests in both Merced and in Palmdale, CA agricultural soils, the sensors responded to introduced nitrate pulses, but with different dynamics relative to the larger commercial sensors. These experiments are on-going but suggest a form factor (size, shape) effect of the sensor when deployed in a porous medium such as soil.

To fill the need for a miniature reference electrode, we identified and tested one commercial version (Cypress Systems, ESA Mini-reference electrode) which works well but is expensive (\$190). To create an inexpensive miniature reference electrode, we are exploring the use of AgCl-coated silver wire. This electrode is not a “true” reference electrode; however, it can be calibrated once versus a commercial reference electrode at the time of deployment in soil. Thus, only one commercial reference electrode would suffice to support a multiple sensor deployment.

BARD Research Grant Final Scientific Report

Scientific background

Increasing soil salinity threatens the sustainability of agriculture in many arid and semi-arid climates in Israel, the western U. S., and globally. This research aimed at creating scaleable (i.e., inexpensive with low power needs) sensors for *in situ* deployment and monitoring nitrate concentrations in soil moisture. A nitrate sensor for deployment in agricultural soils is challenging to develop relative to sensors for other ions due its nonspecific binding to other ligands and absence of characteristic bands associated with spectroscopic techniques. Currently commercially available nitrate selective electrodes are relatively expensive (\$300-\$400 each), have short lifetime (a few months) and are mainly fabricated for fluid probing under relatively clean conditions. Advances in conducting polymers and the advent of micro- and nano-fabrication technology offer an opportunity for creating scaleable, highly selective microsensors that can be engineered for *in situ* deployment in soils. This work takes advantage of ion recognition by conducting polymers using molecular imprinting for sensing of nitrate under real environmental conditions in an agricultural setting.

Significance of main scientific achievements or innovations.

This 1-year feasibility study results in several significant achievements. First and most importantly, we have created a working prototype of a scaleable nitrate sensor which can be deployed in soils. More specific accomplishments related to this achievement include the following:

- A double-layer nitrate sensor where the Ppy inner layer is covered by a PEDOT outer layer was developed. This configuration stabilize the sensor (see appendix Figure 1).
- A sensor packaging approach was developed for deploying Ppy nitrate sensors and miniature reference electrodes in soil, and for acquiring sensor responses using commercial data acquisition hardware (wireless and self-logging).
- The selectivity coefficients for Ppy-based nitrate sensors were quantified for a range of potential interfering ions (see appendix Tables 1 and 2). Two potential solutions for the problem of developing inexpensive reference electrodes were also identified and tested.
- The packaged nitrate microsensors were successfully tested in field tests at two different sites (see appendix Figures 2 and 3).

**BARD Research Grant
Final Scientific Report**

- A second successful nitrate sensor was developed based on the EDOT polymer (which was previously thought to be infeasible).
- Feasibility tests ruled out the use of the proposed polypyrrole analogs (polymers 1 and 2—structures given below).

In this 1-year feasibility study, we tried polymerization of several different monomers, commercial as well as novel, specially designed and synthesized for this project in the presence of the nitrate ion to produce imprinted conductive polymers. Polymers 1 and 2 (shown below) produced a response to nitrate, but one inferior to that produced by a polypyrrole (Ppy)-based sensor (which we demonstrated prior to this study). Thus, we elected to proceed with improving the stability of the Ppy-based sensor.

In order to improve stability of the Ppy-based sensor, we created a two-layer design which includes nitrate-doped Ppy as an inner layer, and nitrate-doped PEDOT as the outer layer. PEDOT is known for its high environmental stability and conductivity. This design has demonstrated promise, but is still undergoing optimization and stability testing.

Previously we had failed to create nitrate-doped PEDOT in the absence of a Ppy layer. Nitrate-doped PEDOT should be very promising for sensor applications due to its high stability and exceptional sensing properties as we showed previously for sensing of perchlorate ions (by perchlorate-doped PEDOT). During this year, we have succeeded in preparing nitrate-doped PEDOT (4 below) by designing a new starting monomer (compound 3 below) for polymerization. We are currently testing this design for nitrate sensing.

In parallel with the fabrication design studies, we fabricated and tested nitrate-doped Ppy sensors in a series of flow studies under laboratory and field conditions. Nitrate-doped Ppy sensors are less stable than is desirable but provide excellent nitrate sensing characteristics for

**BARD Research Grant
Final Scientific Report**

the short-term experiments focusing on packaging and deployment strategies. The fabricated sensors were successfully interfaced with a commercial battery-powered self-logging (Onset Computer Hobo Datalogger) and a wireless data acquisition and transmission system (Crossbow Technologies MDA300 sensor interface and Mica2 wireless mote). In a series of flow-through experiments with water, the nitrate-doped Ppy sensors were exposed to pulses of dissolved nitrate and compared favorably with an expensive commercial sensor. In 24-hour field tests in both Merced and in Palmdale, CA agricultural soils, the sensors responded to introduced nitrate pulses (see Appendix Figures 2 and 3), but with different dynamics relative to the larger commercial sensors. These experiments are on-going but suggest a form factor (size, shape) effect of the sensor when deployed in a porous medium such as soil.

To fill the need for a miniature reference electrode, we identified and tested one commercial version (Cypress Systems, ESA Mini-reference electrode) which works well but is expensive (\$190). To create an inexpensive miniature reference electrode, we are exploring the use of AgCl-coated silver wire. This electrode is not a “true” reference electrode; however, it can be calibrated once versus a commercial reference electrode at the time of deployment in soil. Thus, only one commercial reference electrode would suffice to support a multiple sensor deployment.

Agricultural and/or economic impacts of the research findings, if known.

Observing chemical transport in agricultural soils is important in managing nutrients such as nitrate, and in the minimization of their negative effects on the environment. The proposed research is creating a scaleable (i.e., inexpensive with low power needs) nitrate sensors which is needed to assess distributed (non-point source) problems like that associated with the application of fertilizers.

Details of cooperation: whether and how project objectives were promoted as a result of the cooperation.

The Israeli team developed new sensors, while in parallel the US team developed the sensor packaging and deployment techniques. Close collaboration on a unique combination of synthetic organic chemistry, sensor development and field testing was critical to our success. The nature of this research clearly demands input from both teams, one from the fundamental chemistry side of the problem, the other from the environmental deployment side of the problem. Visits by the Israeli team to Merced (Feb 2006) and the U.S. team to Rehovot (July 2006) were crucial to knowledge transfer and the overall success of this highly collaborative effort. Either team alone would never produce a nitrate sensor working in real soils.

**BARD Research Grant
Final Scientific Report**

List of Publications:

Published papers (acknowledgment to BARD included in all papers):

Sanjio S. Zade and Michael Bendikov, Cyclic Oligothiophenes: Novel Organic Materials and Models for Polythiophene. A Theoretical Study, *J. Org. Chem.* **2006**, *71*, 2972-2981.

Sanjio S. Zade and Michael Bendikov, Theoretical Study of Long Oligothiophene Dications: Bipolaron vs. Polaron Pair vs. Triplet State, *J. Phys. Chem. B* **2006**, *110*, 15839-15846.

BARD Research Grant Final Scientific Report

Contents of the Appendix:

- 1) Table 1 – Results from PPy-based nitrate sensor selectivity tests.
- 2) Table 2 – Comparison of PPy-based nitrate sensor selectivity constants with commercial and literature values.
- 3) Figure 1 – Results from bi-layer sensor (PPy coated with bisEDOT) approach for increasing environmental robustness and longevity.
- 4) Figure 2 – Field setup for nitrate sensors proof-of-concept test at Palmdale, California experimental agricultural site.
- 5) Figure 3 – Results from Palmdale field proof-of-concept test.

Table 1. Values of selectivity coefficients of proposed electrodes towards nitrate ion in presence of various interferent anions. Each value for doped PPy based sensors is a maximum value of $K_{NO_3^-, J^-}^{Pot}$ out of 6 electrodes studied (concentration of interfering anion was 1×10^{-2} M).

J^-	$K_{NO_3^-, J^-}^{Pot}$	
	PPy(NO ₃) pencil lead -based ISE	PPy(NO ₃) glassy carbon - based ISE [1]
HCO ₃ ⁻	3.8×10^{-3}	-
Cl ⁻	1.20×10^{-2}	5.7×10^{-2}
PO ₄ ³⁻	2.00×10^{-4}	9.0×10^{-4}
Br ⁻	9.10×10^{-2}	7.6×10^{-2}
NO ₂ ⁻	2.22×10^{-4}	-
ClO ₄ ⁻	2.93×10^{-3}	5.7×10^{-2}

Table 2. Comparison of the $K_{NO_3^-, ClO_4^-}^{Pot}$ observed for perchlorate using three commercial nitrate electrodes and PPy(NO₃) based electrode ([1] R.S. Hutchins, L.G. Bachas, *Anal. Chem.* 67 (1995) 1654).

Electrode	$K_{NO_3^-, ClO_4^-}^{Pot}$
Orion model 92-07 [2]	1000
Corning Model 477316 [2]	800
Sentek Nitrate ISE [3]	16.2
PPy(NO ₃) pencil lead based	2.93×10^{-3}

[2] Y. Umezawa, In *CRC Handbook on Ion-Selective Electrodes: Selectivity coefficients*; CRC Press: Boca Raton, FL, 1990; pp 89,99.

[3] Sentek: *Nitrate Ion-Selective electrode*, operating instructions, p.9 (<http://www.sentek.co.uk/>).

Figure 1. Calibration curves for bi-layer (PPy-BisEDOT) nitrate sensors over time (PPy nitrate sensor is also included for comparison).

BARD Research Grant Final Scientific Report

Bi-layer (PPy-BisEDOT) nitrate sensor (green curve) is clearly more stable than PPy-based nitrate sensor (red curve).

Figure 2. Field-testing of PPy-based nitrate sensors at the Palmdale, CA experimental field site.

Two PPy-based nitrate sensors fabricated on mechanical pencil leads were placed at depths of 7 and 15 cm below the ground surface (see Figure 1—the diagonal white tube serves as a conduit connecting sensors to data-logging hardware). A nitrate solution was then applied to the soil surface, and irrigation was initiated using the center pivot device shown in the background.

The results for this proof-of-concept experiment are shown below in Figure 2. Regarding the irrigation schedule, the shaded region in the plot represents an intense irrigation event of approximately 2.5 hours. The arrows denote regular irrigation events in which the center pivot device passes over the experimental plot approximately once per 6 hours for a irrigation duration of about 10 min.

As the two sensor responses indicate, there is a rather chaotic response during the intense watering event. However, at the end of this event there is a clear voltage drop for both sensors, indicating the arrival of the nitrate pulse being driven down from the surface soils.

Subsequent irrigation events are also evident as residual from the nitrate pulse is being cleared from the depths associated with the sensors and pushed deeper into the soil.

**BARD Research Grant
Final Scientific Report**

Figure 3. Results from the in situ PPy-based nitrate sensor deployments in Palmdale, CA.